N500

Nepheline Syenite

Nules, Spain

Analytical Chemistry

			Method
SiO_2	55.5	%	XRF
Al_2O_3	24.5	%	XRF
Fe_2O_3	0.11	%	XRF
CaO	1.26	%	XRF
Na_2O	8.05	%	XRF
K_2O	8.80	%	XRF
TiO_2	0.17	%	XRF
MgO	0.03	%	XRF
LOI	1.2	%	950ºC
Moisture	0.15	%	110ºC

Other parameters

Sieve (µm) Cumulative retained			Method
600	0	%	Seives
500	0.7	%	Seives
40	98	%	Seives

Information and Customer service

Tel. +34 864 80 94 00

customersupport.es@sibelco.com

The data in this document is based on an average of our standard production and is determined using Sibelco's standard test methods. Since the product is based on a natural material, we reserve the right to change this information when necessary. Safety information accompanying this product is available in the form of an SDS. All sales are made strictly in accordance with our "General Conditions of Sale", available upon request, or with a written sales agreement duly signed by us

The globe mark is a trademark of SCR-Sibelco®, its subsidiaries and affiliates. A list of Sibelco group companies and their registered addresses is available at SCR-Sibelco NV, Plantin en Moretuslei 1A, 2018 Antwerp, Belgium. Company No: 0404.679.941